

DSET LABORATORIES

A Division of Atlas Material Testing Technology LLC
45601 North 47th Avenue
Phoenix, Arizona 85087 U.S.A.
Phone: +1 623-465-7356
Toll Free: 800-255-3738 (U.S. only)
Fax: +1 623-465-9409
www.atlas-mts.com

Report No.: 37257-0
Order No.: AE37257
Client Reference: P.O. #: 20171
Date: May 16, 2017

**HEMISPHERICAL SPECTRAL REFLECTANCE
TEST REPORT**

prepared for:

THE ULTIMATE COATINGS COMPANY
2801-B Vassar Street
Reno, NV 89502


presented by:

Atlas Weathering Services Group
45601 North 47th Avenue
Phoenix, AZ 85087-7042
Phone: 623-465-7356

This test report contains only findings and results arrived at after employing the specific test procedures and standards listed herein. It does not constitute a recommendation for, endorsement of, or certification of the product or material tested. Atlas Weathering Services Group makes no warranty, expressed or implied, except that the test has been performed, and a report prepared, based upon the sample or samples furnished by the client. Extrapolation of data from the sample or samples relating to the batch or lot from which it was obtained may not correlate and should be interpreted accordingly with extreme caution. We assume no responsibility for variations in quality, composition, appearance, performance, or other feature of similar subject matter produced by persons or under conditions over which we have no control. This report shall not be reproduced except in full without the written approval by Atlas Weathering Services Group.


This report contains 4 pages

Prepared by:



Erika Wunderlich
Group Leader, Evaluations Services

Approved by:



Jaynae Bushong
Group Leader, Static Services

DSET LABORATORIES

A Division of Atlas Material Testing Technology LLC
45601 North 47th Avenue
Phoenix, Arizona 85087 U.S.A.
Phone: +1 623-465-7356
Toll Free: 800-255-3738 (U.S. only)
Fax: +1 623-465-9409
www.atlas-mts.com

THE ULTIMATE COATINGS COMPANY

Report No.: 37257-0
Order No.: AE37257
Client Reference: P.O. #: 20171
Date: May 16, 2017
Page 2 of 4

**HEMISPHERICAL SPECTRAL REFLECTANCE
TEST REPORT****1.0 INTRODUCTION**

This report presents results of spectral reflectance on the following thirteen painted specimens coded:

1. Thermo-seal 1500 White
2. Thermo-seal 1500 Pearl White
3. Thermo-seal 1500 Byron Beige
4. Thermo-seal 1500 Castlemaine
5. Thermo-seal 1500 Greywynd
6. Thermo-seal 1500 Kangaroo
7. Thermo-seal 1500 Brickland
8. Thermo-seal 1500 Cinnemoie
9. Thermo-seal 1500 Mild Grey
10. Thermo-seal 1500 Brisbane Blue
11. Thermo-seal 1500 Greenstream
12. Thermo-seal 1500 Wallaby
13. Thermo-seal 1500 Joey Grey

2.0 TEST METHODS AND PROCEDURES

Hemispherical spectral reflectance measurements were performed in accordance with ASTM Standard Test Method E903. The measurements were performed with a PerkinElmer Lambda 950 Spectrophotometer utilizing an integrating sphere (Fig X1.3 of E903). Total reflectance measurements were obtained in the solar spectrum from 2500nm to 250nm at an incident angle of 8°. The measurements employ a detector-baffled, wall-mounted integrating sphere that precludes the necessity of employing a reference standard except to define the instrument's 100% line. The measurements are properly denoted as being 'hemispherical spectral reflectance'.

Total Solar reflectance was obtained by integrating the spectral data against Air Mass 1.5 direct (ASTM G159) solar spectrum utilizing 105 weighted ordinates. All spectral data are submitted herewith in the original.

DSET LABORATORIES

A Division of Atlas Material Testing Technology LLC
45601 North 47th Avenue
Phoenix, Arizona 85087 U.S.A.
Phone: +1 623-465-7356
Toll Free: 800-255-3738 (U.S. only)
Fax: +1 623-465-9409
www.atlas-mts.com

THE ULTIMATE COATINGS COMPANY

Report No.: 37257-0
Order No.: AE37257
Client Reference: P.O. #: 20171
Date: May 16, 2017
Page 3 of 4

**HEMISPHERICAL SPECTRAL REFLECTANCE
TEST REPORT**

3.0 OBSERVATIONS, DEVIATIONS, AND WAIVERS

Measurements were made on the coated side of the specimens.

With all test methods, there typically is a level of uncertainty for the test data due to the acceptable operating tolerances of the instrumentation and variation caused by the test method. The estimated tolerances are expected to be less than plus or minus 2% for most materials tested to ASTM E903.

CAUTION: ASTM Test Method E903, paragraph 5.4 clearly states “this test method has been found practical for smooth materials... Materials that are textured, inhomogeneous, patterned, or corrugated require special consideration”. In that, the specimen exhibits inhomogeneities, and the client is cautioned when utilizing the reported measurements.

DSET LABORATORIES

A Division of Atlas Material Testing Technology LLC
 45601 North 47th Avenue
 Phoenix, Arizona 85087 U.S.A.
 Phone: +1 623-465-7356
 Toll Free: 800-255-3738 (U.S. only)
 Fax: +1 623-465-9409
 www.atlas-mts.com

THE ULTIMATE COATINGS COMPANY

Report No.: 37257-0
 Order No.: AE37257
 Client Reference: P.O. #: 20171
 Date: May 16, 2017
 Page 4 of 4

HEMISPHERICAL SPECTRAL REFLECTANCE TEST REPORT

4.0 RESULTS

Specimen Code	% Solar Reflectance
1. Thermo-seal 1500 White	89.9
2. Thermo-seal 1500 Pearl White	78.2
3. Thermo-seal 1500 Byron Beige	69.8
4. Thermo-seal 1500 Castlemaine	61.5
5. Thermo-seal 1500 Greywynd	68.8
6. Thermo-seal 1500 Kangaroo	53.8
7. Thermo-seal 1500 Brickland	47.9
8. Thermo-seal 1500 Cinnemoie	37.8
9. Thermo-seal 1500 Mild Grey	64.8
10. Thermo-seal 1500 Brisbane Blue	53.1
11. Thermo-seal 1500 Greenstream	30.0
12. Thermo-seal 1500 Wallaby	55.6
13. Thermo-seal 1500 Joey Grey	46.9